

fabric, for example fine mica or mica paper, with a weight per unit area which is a multiple of the weight per unit area of the fabric. The proportion by weight of the dielectrically high quality material determines the quality, especially the breakdown strength, of insulation produced from the insulating tape.--.

Page 3, delete the paragraph, beginning on line 32 and ending on line 33.

Page 3, after line 33, insert the following:

--BRIEF DESCRIPTION OF THE DRAWING

The drawing figure shows an embodiment of the invention.-

Page 5, replace the table, beginning on line 1, as follows:

Insulating tape	1 (Prior art)	2 (Prior art)	3 Invention
Weight per unit area, g/cm ²	23	33	24
Warp thread weight, tex	5.5	11	11
Woof thread weight, tex	5.5	5.5	5.5
Thread density, warp threads, per cm	27	24	16
Thread density, woof threads, per cm	15	11	10
Tensile strength in warp direction, N/cm	80	140	104
Edge tear initiation strength, N	8	16	16
Porosity, glass side, s/100 ml	100	180	100